

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

Claim 1 (currently amended): A process for preparing a homopolymer or copolymer having a melt flow index (MFR 190/15) of from 1.3 g/10 min to 10 g/10 min, a molecular weight distribution M_w/M_n of from 3 to 30, a bulk density of from 0.05 g/cc to 0.4 g/cc and a an average particle size of from 5 μm to 300 μm by polymerization of the monomers using a mixed catalyst prepared by reacting a Ti(IV) compound with an organic aluminum compound at from 20°C to 50 °C in a suspension medium for from 0.5 minute to 60 minutes.

Claim 2 (currently amended): The process for preparing a homopolymer or copolymer as claimed in claim 1, wherein the melt flow index (MFR 190/15) is from 1.3 g/10 min to 10 g/10 min, the molecular weight distribution M_w/M_n is from 3 to 10, the bulk density is from 0.1 g/cc to 0.4 g/cc and the average particle size is from 20 μm to 200 μm .

Claim 3 (currently amended): The process for preparing a homopolymer or copolymer as claimed in claim 1, wherein the melt flow index (MFR 190/15) is from 1.4 g/10 min to 5 g/10 min, the molecular weight distribution M_w/M_n is from 4 to 8, the bulk density is from 0.13 g/cc to 0.3 g/cc and the average particle size is from 60 μm to 180 μm .

Claim 4 (currently amended): The process for preparing a homopolymer or copolymer as

claimed in claim 1, wherein the melt flow index (MFR 190/15) is from 1.4 g/10 min to 3 g/10 min, the molecular weight distribution M_w/M_n is from 4 to 8, the bulk density is from 0.15 g/cc to 0.28 g/cc and the average particle size is from 60 μm to 160 μm .

Claim 5 (previously amended): The process for preparing a homopolymer or copolymer as claimed in claim 1, wherein the polymerization is carried out at a temperature of from 30°C to 130°C and a pressure of from 0.05 MPa to 4 MPa.

Claim 6 (previously amended): The process for preparing a homopolymer or copolymer as claimed in claim 1, wherein the polymerization is carried out at a temperature of from 50°C to 90°C.

Claim 7 (previously amended): The process for preparing an ethylene homopolymer or copolymer as claimed in claim 1, wherein the concentrations of the reactants in the starting solutions in the preparation of the mixed catalyst are from 0.1 mol to 9.1 mol of Ti(IV) compound/l of solvent and from 0.01 mol to 1 mol of Al compound/l.

Claim 8 (cancelled)

Claim 9 (cancelled)

Claim 10 (cancelled)

Claim 11 (cancelled)

Claim 12 (cancelled)